

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 1 184 194 A2**

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
**06.03.2002 Bulletin 2002/10**

(51) Int Cl.7: **B41M 5/00**

(21) Application number: **01203140.7**

(22) Date of filing: **20.08.2001**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE TR**  
Designated Extension States:  
**AL LT LV MK RO SI**

(30) Priority: **31.08.2000 US 652234**

(71) Applicant: **EASTMAN KODAK COMPANY**  
**Rochester, New York 14650 (US)**

(72) Inventor: **Wexler, Allan**  
**Rochester, New York 14650-2201 (US)**

(74) Representative:  
**Nunney, Ronald Frederick Adolphe et al**  
**Kodak Limited, Patents, W92-3A, Headstone**  
**Drive**  
**Harrow, Middlesex HA1 4TY (GB)**

(54) **Ink jet recording element**

(57) An ink jet recording element comprising a support having thereon, in the order recited, at least one base layer comprising a hydrophilic or porous material and a porous top layer capable of either retaining or transporting an ink image, the porous top layer comprising a polymeric binder and thermally-compliant core-shell particles, the particle-to-binder ratio being between 95:5 and 50:50, and wherein each thermally-compliant core-shell particle has:

a) a shell of inorganic colloidal particles, and

b) a core of a thermoplastic polymer,

the particles having a particle size between 0.5  $\mu\text{m}$  and 10  $\mu\text{m}$ , the polymeric core having a softening point of greater than 50 ° C, and the weight ratio of the shell of the inorganic colloidal particles to the thermoplastic core being from 1:5 to 1:99.

**EP 1 184 194 A2**

## Description

[0001] This invention relates to an ink jet recording element, more particularly to an ink jet recording element which contains thermally compliant composite particles having a core-shell structure.

[0002] In a typical ink jet recording or printing system, ink droplets are ejected from a nozzle at high speed towards a recording element or medium to produce an image on the medium. The ink droplets, or recording liquid, generally comprise a recording agent, such as a dye or pigment, and a large amount of solvent. The solvent, or carrier liquid, typically is made up of water, an organic material such as a monohydric alcohol, a polyhydric alcohol or mixtures thereof.

[0003] An ink jet recording element typically comprises a support having on at least one surface thereof at least one ink-receiving layer. The ink-receiving layer is typically either a porous layer that imbibes the ink via capillary action, or a polymer layer that swells to absorb the ink. Swellable hydrophilic polymer layers take an undesirably long time to dry so that porous layers which dry more rapidly are generally regarded as superior. Ink jet recording elements may contain several layers on the support. Typical two layer constructions have either an uppermost ink transporting layer in combination with an ink retaining underlayer, or an uppermost ink image capture layer in combination with an underlying ink vehicle sump layer.

[0004] Porous layers typically contain an easily wettable but water insoluble refractory inorganic pigment as well as a binder. Typically these refractory inorganic pigment particles are comprised of either silica or alumina. The high loading of these easily wettable but refractory particles and the presence of numerous voids, which are essential to the rapid ink absorption of the layer, presents a problem in that the many interfaces presented by such a layer leads to light scattering and results in insufficient gloss. To reduce the scattering of light and thereby improve gloss, porous layers are often comprised principally of colloidal, i.e., less than  $0.5\mu$ , particles. However, these particles are difficult to coat without cracking of the coated layer. Thus it is difficult to achieve high gloss with refractory particles larger than  $0.5\mu$ , and conversely it has proven difficult to coat a non-cracking layer with refractory particles smaller than  $0.5\mu$ .

[0005] U.S. Patent 5,576,088 relates to an ink jet recording sheet having at least one ink-receiving layer and a gloss-providing layer consisting of a synthetic polymer latex binder and a pigment, at least 70% by weight of which is colloidal particles. The gloss-providing layer may be calendered or pressure contacted to a heated specular roll immediately after coating to further enhance the gloss. However, there are problems with this recording sheet in that the use of organic particles decreases the releasability of the gloss-providing layer from the specular roll. Further, calendering the layer prior to imaging decreases ink penetrability. In addition, the above layers have a high loading of colloidal particles so that the layers are prone to cracking due to high drying stresses.

[0006] U.S. Patent 5,472,773 relates to a coated paper comprising a substrate with a surface layer of colloidal aggregates alumina crystals (or pseudo-boehmite) and a binder having a specular gloss at  $60^\circ$  of at least 30%. However, there are problems with this coated paper in that this gloss level is less than desirable for high quality imaged substrates and preparing the coated paper requires a costly and complex layer transfer technology.

[0007] EP 0 813 978 A1 discloses a porous ink jet recording sheet having solid fine particles in a hydrophilic binder with oil drops to reduce layer brittleness and cracking. However, there is a problem with this element in that oil drops can be exuded from the coating to give an unwanted oily surface feel and diminished gloss.

[0008] It is an object of this invention to provide an ink jet recording element having a porous top layer that can either transport or retain an ink image, and which can be heat and pressure treated to a high gloss despite the refractory nature of incorporated inorganic pigment particles. Another object of the invention is to provide a glossable ink jet recording element which can be coated and dried without cracking and yet maintain good ink absorptivity.

[0009] These and other objects are provided by the present invention which relates to an ink jet recording element comprising a support having thereon, in the order recited, at least one base layer comprising a hydrophilic or porous material and a porous top layer capable of either retaining or transporting an ink image, the porous top layer comprising a polymeric binder and thermally-compliant core-shell particles, the particle-to-binder ratio being between 95:5 and 50:50, and wherein each thermally-compliant core-shell particle has:

- a) a shell of inorganic colloidal particles, and
- b) a core of a thermoplastic polymer,

the particles having a particle size between  $0.5\mu$  and  $10\mu$ , the polymeric core having a softening point of greater than  $50^\circ\text{C}$ , and the weight ratio of the shell of the inorganic colloidal particles to the thermoplastic core being from 1:5 to 1:99

[0010] By use of the invention, an ink jet recording element is provided which has a high gloss, does not crack and has good ink absorptivity.

[0011] The composite thermally-compliant core-shell particles used in the invention may be prepared by several procedures including evaporative limited coalescence, as described in U.S. Patent 4,833,060 and limited coalescence, as described in U.S. Patent 5,354,799. In both of these preparations, the shell is formed in-situ by a promoter during

the preparation of the particle. Alternatively, the shell may be assembled via the layer-by-layer technique on preformed particles as described in "Electrostatic Self-Assembly of Silica Nanoparticle-Polyelectrolyte Multilayers of Polystyrene Latex Particles" in the Journal of the American Chemical Society, vol. 120, p. 8523 (1998).

**[0012]** The thermoplastic core polymer employed in the invention has a softening point greater than 50 ° C, and preferably between 50 ° C and 120 ° C. A softening point of a polymer can be measured by the Ring and Ball method as described in ASTM E28.

**[0013]** In a preferred embodiment of the invention, the thermoplastic core polymer is a polyester, an acrylic polymer or a styrenic polymer. Examples of these polymers include an amorphous polyester Kao C® (Kao Corp.), an acrylic polymer such as Carboset 526® (BF Goodrich Specialty Chemicals), or a styrene allyl alcohol copolymer such as SAA 100® (Lyondell Chemical Co.).

**[0014]** If the limited coalescence process is used to prepare the composite particles employed in the invention, then monomers and polymerization conditions should be chosen which will polymerize to form a core polymer with a softening point as described above. Suitable monomers include styrenic and vinyl monomers such as styrene, methylmethacrylate or butylacrylate. Mixtures of monomers, such as styrene, butylacrylate and methylmethacrylate may be polymerized to obtain the desired polymer properties.

**[0015]** Suitable colloidal inorganic particles which can be used as the shell material in the invention include colloidal silicas and modified colloidal silicas available from DuPont as Ludox®, and colloidal aluminas such as Dispal® (Condea Corp.). The size of the colloidal inorganic particles may range from 5 to 100nm.

**[0016]** The shell of the core-shell particle used in the invention can be further modified, after formation of the primary core-shell particle, to alter a number of particle properties such as the surface charge on the particles. If the upper layer is to be ink retentive, then the surface charge on the particle should be opposite to that of the colorant. If an anionic or negative dye, for example, is the colorant, then the particle charge should be cationic or positive, so as to mordant the dye in the layer. Conversely, if the upper layer is to be ink transporting, then the surface charge on the particle should be rendered either neutral or the same as that of the dye. Surface charge on the particles can be measured via the electrokinetic sonic amplitude (ESA) technique as described in J. Colloid and Interface Science, 173, 406, (1995).

**[0017]** As stated above, the weight ratio of the shell of the inorganic colloidal particles to the thermoplastic core is from 1:5 to 1:99, preferably from 1:15 to 1:50. The % silica is determined, on a sample washed free of unadhered colloidal silica, using 14-MeV neutron activation analysis to measure the Si content as described in "Activation Analysis with Neutron Generators" S. Nargolwalla and E. Przybylowicz eds. John Wiley & Sons, Inc. (1973), p. 528.

**[0018]** Also as stated above, the particle size of the core-shell particle used in the invention has a particle size between 0.5 and 10 µm, preferably from 0.9 to 5 µm. The particle size of the core-shell particle is determined by a Horiba LA-920 Laser Scattering Particle Size Distribution Analyzer (Horiba Instruments, Inc.) and is a volume-weighted mean size.

**[0019]** A core-shell particle having a negative surface charge, by virtue of an adherent layer of a negatively charged colloidal silica, can be rendered neutral or cationic by use of cationic surfactants as described in Colloids and Surfaces, 28, (1987) 159-168 and references contained therein. Water-soluble cationic polymers, such as poly(diallyl dimethylammonium) chloride or cationic colloidal latex particles, can be used to modify the surface charge of the core-shell particle as described in the above-referenced article in the Journal of the American Chemical Society. Core-shell particles having a cationic surface charge by virtue of an adherent layer of cationically charged colloidal silica, can be rendered anionic by similar procedures. Further, the surface charge and wetting properties of the silica shell can be modified by treatment with a variety of silanes as described in Chemtech, 7, 766-778 (1977).

**[0020]** The polymeric binder useful in the recording element of the invention is not particularly limited. Any polymer or mixture of polymers, which are film formers and function to bind the particles described above to form a coherent layer on coating, will be useful. Examples of such binders include water soluble polymers such as gelatin, poly(vinyl alcohol), poly(ethylene oxide), poly(2-ethyl-2-oxazoline), cellulosic polymers such as methyl cellulose, emulsion polymers and copolymers such as ethylene-vinyl chloride, poly(acrylates), poly(vinylacetate), polyvinylidene chloride, vinylacetate-vinyl chloride, and aqueous polymer dispersions such as polyurethanes and polyurethane alloys.

**[0021]** As stated above, the particle-to-binder ratio is between 95:5 and 50:50, preferably between 90:10 and 80:20. If the particle-to-binder ratio is above the range stated, the layer will not have any cohesive strength. If the particle-to-binder ratio is below the range stated, the layer will not be porous enough to provide a fast dry time.

**[0022]** The base layer or layers, in general, will have a thickness of 1 µm to 50 µm, and the top layer will usually have a thickness of 2 µm to 50 µm.

**[0023]** If the uppermost layer is retentive of the ink image, then the base layer will act as a reservoir or sponge layer for the absorption of ink solvent. If the uppermost layer is ink transporting, then the base layer will additionally serve to retain the ink image. The base layer may be hydrophilic and swellable or porous. Generally, the base layer is present in an amount from 1 g/m<sup>2</sup> to 50 g/m<sup>2</sup>, preferably from 5.0 g/m<sup>2</sup> to 30 g/m<sup>2</sup>. Suitable hydrophilic materials include gelatin, acetylated gelatin, phthalated gelatin, oxidized gelatin, chitosan, poly(alkylene oxide), poly(vinyl alcohol), modified poly

(vinyl alcohol), sulfonated polyester, partially hydrolyzed poly(vinylacetate/ vinyl alcohol), poly(acrylic acid), poly(1-vinylpyrrolidone), poly(sodium styrene sulfonate), poly(2-acrylamido-2-methane sulfonic acid), polyacrylamide or mixtures thereof. Copolymers of these polymers with hydrophobic monomers may also be used. Suitable porous materials for a base layer include, for example, silica or alumina in a polymeric binder, including hydrophilic binders such as those described above.

[0024] In a preferred embodiment of the invention, the base layer comprises gelatin which may have up to 15% of another hydrophilic material such as poly(1-vinylpyrrolidone). In another preferred embodiment, the base layer is porous fumed alumina in a crosslinked poly(vinyl alcohol) binder.

[0025] The support used in the ink jet recording element of the invention may be opaque, translucent, or transparent. There may be used, for example, plain papers, resin-coated papers, various plastics including a polyester resin such as poly(ethylene terephthalate), poly(ethylene naphthalate) and poly(ester diacetate), a polycarbonate resin, a fluorine resin such as poly(tetra-fluoro ethylene), metal foil, various glass materials, and the like. In a preferred embodiment, the support is a resin-coated paper. The thickness of the support employed in the invention can be from 12 to 500  $\mu\text{m}$ , preferably from 75 to 300  $\mu\text{m}$ .

[0026] If desired, in order to improve the adhesion of the base layer to the support, the surface of the support may be corona-discharge-treated prior to applying the base layer or solvent-absorbing layer to the support.

[0027] Since the image recording element may come in contact with other image recording articles or the drive or transport mechanisms of image recording devices, additives such as surfactants, lubricants, matte particles and the like may be added to the element to the extent that they do not degrade the properties of interest. In addition, the top layer of the invention may also contain other additives such as viscosity modifiers or mordants.

[0028] The layers described above, including the base layer and the top layer, may be coated by conventional coating means onto a support material commonly used in this art. Coating methods may include, but are not limited to, wound wire rod coating, slot coating, slide hopper coating, gravure, curtain coating and the like. Some of these methods allow for simultaneous coatings of both layers, which is preferred from a manufacturing economic perspective.

[0029] Ink jet inks used to image the recording elements of the present invention are well-known in the art. The ink compositions used in ink jet printing typically are liquid compositions comprising a solvent or carrier liquid, dyes or pigments, humectants, organic solvents, detergents, thickeners, preservatives, and the like. The solvent or carrier liquid can be solely water or can be water mixed with other water-miscible solvents such as polyhydric alcohols. Inks in which organic materials such as polyhydric alcohols are the predominant carrier or solvent liquid may also be used. Particularly useful are mixed solvents of water and polyhydric alcohols. The dyes used in such compositions are typically water-soluble direct or acid type dyes. Such liquid compositions have been described extensively in the prior art including, for example, U.S. Patents 4,381,946; 4,239,543 and 4,781,758.

[0030] The following examples further illustrate the invention.

#### Example 1

#### Preparation of Core-Shell Particles of the Invention

##### 1) 3- $\mu\text{m}$ Particles With a Colloidal Silica Shell and a Polyester Core Prepared via the Evaporative Limited Coalescence Process

[0031] To 225 gm ethyl acetate was added 25 gm of Kao® C polyester resin and stirred to solution. Separately an aqueous solution was prepared of 375 gm pH 4 buffer, 21 gm Ludox TM50® colloidal silica (50 wt.% silica, DuPont Corp.), and 4.5gm of 10% poly(adipic acid-co-methylaminoethanol). The aqueous phase was placed in a Silverson mixer and with the mixer on the organic phase was added and emulsified at 6,000 rev/min for one minute. The emulsion was then passed through a Microfluidizer (Microfluidics Manufacturing model 110T) to further reduce the emulsion droplet size. After evaporating the ethyl acetate, there was obtained a narrowly distributed population of spherical, silica coated, polyester particles  $\mu = 3.0 \pm .36$ . Scanning electron microscopy of a freeze fractured sample showed that the surface of the particles was completely covered by a shell of adherent colloidal silica. Neutron activation analysis of a sample washed free of unadhered colloidal silica gave the weight fraction of the adhered silica shell at 3.9%. The slurry solids therefore comprised 73% core-shell particles and 27% unadhered silica. Sufficient water was decanted to give a 30% solids slurry.

##### 2) 2- $\mu\text{m}$ Particles With a Colloidal Silica Shell and a Polystyrene Core: Prepared via the Limited Coalescence Process

[0032] To 333g styrene was added 10g 2,2'- azobis(2,4-dimethylvaleronitrile), Vazo 52® (DuPont Corp.), and stirred until the Vazo 52® dissolved. Separately, an aqueous phase was prepared by adding to 1000g of distilled water 10.43g potassium hydrogen phthalate, 4g 0.1N HCl, 7.2g poly(adipic acid-co-methylaminoethanol) and 91.5g of Ludox TM®

colloidal silica, and stirred for 15 minutes. The organic phase was then added to the stirred (marine prop agitator) aqueous phase and stirred for 15 minutes. The resultant dispersion was passed through a Gaulin homogenizer twice at 20.7 MPa and then heated at 54C for sixteen hours. Neutron activation analysis of a sample washed free of unadhered colloidal silica gave the weight fraction of the adhered silica shell at 6.6%. The slurry solids therefore comprised 94% core-shell particles and 6% unadhered silica. Solids were adjusted to obtain a 27% solids slurry. There was thereby obtained a narrowly distributed population of silica coated polystyrene particles  $\mu = 2.0 \pm .36$  microns.

### 3) 6- $\mu$ m Particles With a Colloidal Silica Shell and a Polyester Core Prepared via the Evaporative Limited Coalescence Process

[0033] The same procedure was used as above in 1) except that the aqueous phase had 375g pH 4 buffer, 5.0g Ludox TM<sup>®</sup> colloidal silica, and 1.1g of 10% poly(adipic acid-co-methylaminoethanol). After evaporating the ethyl acetate, there was obtained a narrowly distributed population of silica coated polyester particles  $\mu = 6.4 \pm .36$ . Neutron activation analysis of a sample washed free of unadhered colloidal silica gave the weight fraction of the adhered silica shell at 2.1%. The slurry solids therefore comprised 93% core-shell particles and 7% unadhered silica. Sufficient water was decanted to give a slurry with 30% solids.

### 4) 2- $\mu$ m Particles With a Colloidal Silica Shell and a Polystyrene Core: Prepared via the Limited Coalescence Process and Surface Charge Modified With a Colloidal Cationic Latex

[0034] To 15.1g of the 27% solids slurry prepared as above in 2) was added 1.7g of a 15% solids cationic 100nm colloidal latex dispersion of divinylbenzene-co-N-vinylbenzyl-N,N,N-trimethylammonium chloride. ESA titration gave an equivalence point of 0.033g 15% latex per gram solids.

### 5) 2- $\mu$ m Particles With a Colloidal Silica Shell and a Polystyrene Core: Prepared via the Limited Coalescence Process and Surface Charge Modified With a Cationic Water-Soluble Polymer

[0035] To 15.1g of the 27% solids slurry prepared as above in 2) was added 1.7g of a 0.2% aqueous solution of poly (diallyl dimethylammonium chloride) (Aldrich Corp.). ESA titration gave an equivalence point of 0.05g 0.2% polymer per gram solids.

### 6) 2- $\mu$ m Particles With a Colloidal Silica Shell and a Polystyrene Core: Prepared via the Limited Coalescence Process and Surface Modified by a Silane

[0036] To 20g of the 27% solids slurry prepared as above in 2) was added 0.27g of N-(2-aminoethyl)-3-aminopropylmethyl-dimethoxysilane (United Chemical Technologies, Inc.) and the mixture stirred overnight.

#### C-1 Control Colloidal Silica Particles

[0037] Commercial Ludox TM50 <sup>®</sup>, a 50% dispersion of 22nm silica particles was used.

#### C-2 Control 1 $\mu$ m Silica Gel Particles

[0038] Commercial SyloJet <sup>®</sup> 710A a 20% solids slurry of 1  $\mu$ m silica gel particles was used.

#### C-3 Control 6 $\mu$ m Silica Gel Particles

[0039] Commercial Gasil<sup>®</sup> 23 6  $\mu$ m, silica (Crossfield Limited) was added to sufficient water to give an 18% solids slurry.

#### Solution 1 of the Invention:

[0040] To 9.0g of the 30% solids slurry 1 was added 9.63g of water and 1.37g of Witcobond <sup>®</sup> W215 polyurethane (Witco Corp.) to give a 16% solids slurry having a solids ratio of 80 parts 3  $\mu$ m core-shell particles to 20 parts polyurethane binder.

Solution 2 of the Invention

5 [0041] To 18.2g of the 27% solids slurry 2 was added 0.1g of water and 1.72g of Airflex® 4500 ethylene-vinyl chloride emulsion (Air Products Corp) emulsion to give a 30% solids slurry having a solids ratio of 84 parts 2 µm core-shell particles to 16 parts binder.

Solution 3 of the Invention

10 [0042] To 10.0g of the 27% solids slurry 2 was added 1.37g of Witcobond® W320 polyurethane (Witco Corp.) to give a 28% solids slurry having a solids ratio of 84 parts 2 µm core-shell particles to 16 parts binder.

Solution 4 of the Invention

15 [0043] To 17.4g of deionized water is added, 12g of the 30% solids slurry 3, 20.2g of a 10% poly(vinyl alcohol) solution (Gohsenol® Z200 Nippon Gohsei Corp.), 8.6g of a 10% gelatin solution, 1.55g of a latex polymer, Rhoplex® B-60A, (Rohm and Haas Co.) and 0.3g of a 10% surfactant solution (Olin 10G®) to give a 12% solids slurry having a solids ratio of 48 parts 6 µm core-shell particles to 52 parts binder.

Solution 5 of the Invention

20 [0044] To the aqueous slurry of surface charge modified particles 4) of the invention, was added 2.19g of Witcobond® 215 polyurethane to give a 27% solids slurry.

Solution 6 of the Invention

25 [0045] To the aqueous slurry of surface charge modified particles 5) of the invention, was added 2.19g of Witcobond® 215 polyurethane to give a 27% solids slurry.

Solution 7 of the Invention

30 [0046] To 20.3g of the aqueous slurry of the silane modified particles 6) of the invention was added an additional 7.9g of deionized water. Separately 10g of deionized water was added to 2.74g of Witcobond® 215 polyurethane and this mixture was then added to the stirred particles to give a 16% slurry.

Control Solution C-1

35 [0047] To 9.81g deionized water was added 2.5g 1% potassium hydrogen phthalate, 0.8g 0.01N HCl, 5.22g of C-1, Ludox TM50® colloidal silica, and 1.1g of 10% poly(adipic acid-co-methylaminoethanol). To this stirred suspension was then added 1.37g polyurethane, Witcobond® 215, to give a 16% solids slurry having a solids ratio of 85 parts 22 nm colloidal silica particles to 15 parts polyurethane binder.

Control Solution C-2

45 [0048] To 9.41g deionized water was added 2.5g 1% potassium hydrogen phthalate, 0.8g 0.01N HCl, 3.89g of C-1, Ludox TM50® colloidal silica, and 0.83g of 10% poly(adipic acid-co-methylaminoethanol). To this stirred suspension was then added 3.37g polyurethane, Witcobond® 215 to give a 16% solids slurry having a solids ratio of 63 parts 22nm colloidal silica particles to 37 parts polyurethane binder.

Control Solution C-3

50 [0049] To 11.4g of deionized water was added 18g of the 20% solids slurry of control particles C-2, 1.55g of a latex polymer, Rhoplex® B-60A, (Rohm and Haas Co), 20.2g of a 10% poly(vinyl alcohol) solution, Gohsenol Z200®, 8.6g of a 10% gelatin solution and 0.3g of a 10% surfactant solution (Olin 10G®) to give a 12% solids slurry having a solids ratio of 50 parts 1 µm silica gel particles to 50 parts binder.

Control Solution C-4

55 [0050] To 18.75g of deionized water is added, 40.0g of the 18% solids slurry of control particles C-3, 40.4g of a 10%

## EP 1 184 194 A2

poly(vinyl alcohol) solution, Gohsenol Z200 ®, 17.2g of a 10% gelatin solution, 3.10g of a latex polymer, Rhoplex® B-60A, and 0.6g of a 10% surfactant solution (Olin 10G ®) to give a 12% solids slurry having a solids ratio of 50 parts 6 µm silica gel particles to 50 parts binder.

### 5 Preparation of Base Layers

**[0051]** A polyethylene resin-coated paper support was corona discharge treated. The support was then coated at 40 ° C with either:

- a) an aqueous solution comprising 6.7% gelatin, and 1.2 % poly(vinyl pyrrolidone), K90 (International Specialty Products Co.) to provide a base layer of 8.6g/m<sup>2</sup>;
- b) an aqueous solution comprising 3.0% gelatin, 0.60% poly(vinyl pyrrolidone), K90 (International Specialty Products Co.) and 0.40% cationic 100nm colloidal latex dispersion of divinylbenzene-co-N- vinylbenzyl- N,N,N - trimethylammonium chloride to provide a base layer of 4.3g/m<sup>2</sup>; or
- c) a first 38 µm underlayer comprising 87% fumed alumina, 9% poly(vinyl alcohol), and 4% dihydroxydioxane crosslinking agent, and on the first underlayer a second 2µm layer comprising 87% fumed alumina, 8% 100nm colloidal latex dispersion of divinylbenzene-co-N- vinylbenzyl- N,N,N - trimethylammonium chloride, 6% poly(vinyl alcohol), and 1% Zonyl ®FSN surfactant (Dupont Corp.).

**[0052]** The solutions were coated over the underlayers using a wire wound rod, calibrated to give a wet laydown of 120 µm and air dried to form Elements 1 -8 of the Invention and Control Elements 1-3. The 60° gloss was then measured using a micro-TRI-gloss reflectometer (BYK Gardener Corp.).

### Fusing

**[0053]** The coatings were fused in a heated nip at 150°C and 4.2 kg/cm<sup>2</sup> either against:

- a) A 75 µm polyimide film sheet Kapton® (DuPont) at 45.7 cm/min or,
- b) A sol-gel coated polyimide Kapton® (DuPont) belt at 63.5 cm/min.

**[0054]** After cooling to room temperature, the fused composite was separated and the 60° gloss was measured again. The following results were obtained:

Table 1

Element	Particle	Coating Solution	Base Layer	Fusing	Gloss Before	Gloss After
1	3 µm Core-Shell	1	a	a	2.5	87.9
1	3 µm Core-Shell	1	a	b	2.4	96.5
2	2 µm Core-Shell	2	a	a	2.6	91.4
3	2 µm Core-Shell	3	c	b	2.4	89.7
4	6 µm Core-Shell	4	b	a	3	67.4
5	2 µm Core-Shell	5	a	b	2.4	81.4
6	2 µm Core-Shell	5	b	b	2.4	82.4
7	2 µm Core-Shell	6	a	a	2.4	64.2
8	2 µm Core-Shell	7	a	a	2.6	68.9
C-1	22 nm silica	C1	a	a	6.3	9.1
C-2	22 nm silica	C2	a	a	3.2	11.9
C-3	1 µm silica gel	C3	b	b	2.6	3.0
C-4	6 µm silica gel	C4	b	a	2.4	2.7
C-4	6 µm silica gel	C4	b	b	2.4	2.8

**[0055]** The above results show that the elements of the invention provided high gloss as compared to the control

elements.

#### Example 2 - Layer Cracking and Ink Receptivity

**[0056]** The elements were imaged with a Hewlett-Packard Photosmart ® printer with a 9mm by 8mm rectangular test patch for each of the primary and secondary colors at 100% ink coverage. The printed elements were then examined for Ink Absorptivity in accordance with the following evaluation standards.

- A: No deformation of the rectangular pattern with sharp edges of the pattern maintained.
- B: The rectangular pattern was slightly rounded with smooth edges
- C: Major spreading and deformation of the rectangular pattern with ragged edges
- D: Puddling of the ink on the surface

For good ink absorptivity an evaluation of A or B is necessary.

**[0057]** Layer Integrity was evaluated on the above printed elements in both the printed and unprinted regions by observing the layer surface with an eight power magnifying lens according to the following criteria:

- A: No cracks observed
- B: Some cracks observed, but no practical problem in image quality.
- C: Cracks observed, and problem in image quality, but no cracks observed unaided visually.
- D: Cracks observed unaided visually, and serious problems in image quality.

For good Layer Integrity an evaluation of A or B is necessary. The following results were obtained:

Table 2

Element	Particle	Binder (%)	Layer Integrity	Ink Absorptivity
1	3 $\mu$ m core-shell	15	A	A
2	2 $\mu$ m core-shell	15	A	A
C-1	5 nm silica	15	D	A
C-2	5 nm silica	37	A	D

**[0058]** The above results show that the elements of the invention had good layer integrity and ink absorptivity relative to the controls. Specifically, no cracking was found for Elements 1 and 2, which have the same weight fraction binder as Control element C-1, which cracks severely. Control element C-2, with a higher weight fraction binder, did not crack but had very poor ink receptivity.

#### Claims

1. An ink jet recording element comprising a support having thereon, in the order recited, at least one base layer comprising a hydrophilic or porous material and a porous top layer capable of either retaining or transporting an ink image; said porous top layer comprising a polymeric binder and thermally-compliant core-shell particles, the particle-to-binder ratio being between 95:5 and 50:50, and wherein each said thermally-compliant core-shell particle has:

- a) a shell of inorganic colloidal particles, and
- b) a core of a thermoplastic polymer,

said particles having a particle size between 0.5  $\mu$ m and 10  $\mu$ m, said polymeric core having a softening point of greater than 50°C, and the weight ratio of the shell of said inorganic colloidal particles to said thermoplastic core being from 1:5 to 1:99.

2. The ink jet recording element of Claim 1 wherein said base layer comprises gelatin, acetylated gelatin, phthalated gelatin, oxidized gelatin, chitosan, poly(alkylene oxide), poly(vinyl alcohol), modified poly(vinyl alcohol), sulfonated polyester, partially hydrolyzed poly(vinylacetate/ vinyl alcohol), poly(acrylic acid), poly(1-vinylpyrrolidone), poly



(sodium styrene sulfonate), poly(2-acrylamido-2-methane sulfonic acid), polyacrylamide, silica, alumina, or mixtures thereof.

3. The ink jet recording element of Claim 1 wherein said base layer comprises a mixture of gelatin and poly(vinyl pyrrolidone).
4. The ink jet recording element of Claim 1 wherein said base layer comprises a mixture of fumed alumina and crosslinked poly(vinyl alcohol).
5. The ink jet recording element of Claim 1 wherein said base layer has a thickness of 1  $\mu\text{m}$  to 20  $\mu\text{m}$  and said top layer has a thickness of 2  $\mu\text{m}$  to 50  $\mu\text{m}$ .
6. The ink jet recording element of Claim 1 wherein said support is resin-coated paper.
7. The ink jet recording element of Claim 1 wherein said polymeric binder is gelatin, poly(vinyl alcohol), poly(ethylene oxide), poly(2-ethyl-2-oxazoline), methyl cellulose, an ethylene-vinyl chloride copolymer, a polyacrylate, poly(vinyl acetate), poly(vinylidene chloride), a vinyl acetate-vinyl chloride copolymer or a polyurethane.
8. The ink jet recording element of Claim 1 wherein said polymeric binder comprises a polyurethane.
9. The ink jet recording element of Claim 1 wherein said thermoplastic polymer is a polyester, an acrylic polymer or a styrenic polymer.
10. The ink jet recording element of Claim 1 wherein said inorganic colloidal particles are colloidal silica or colloidal alumina.

**THIS PAGE BLANK (USPTO)**

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 1 184 194 A3**

(12)

**EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:  
**06.11.2002 Bulletin 2002/45**

(51) Int Cl.<sup>7</sup>: **B41M 5/00**

(43) Date of publication A2:  
**06.03.2002 Bulletin 2002/10**

(21) Application number: **01203140.7**

(22) Date of filing: **20.08.2001**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE TR**  
Designated Extension States:  
**AL LT LV MK RO SI**

(30) Priority: **31.08.2000 US 652234**

(71) Applicant: **EASTMAN KODAK COMPANY**  
**Rochester, New York 14650 (US)**

(72) Inventor: **Wexler, Allan**  
**Rochester, New York 14650-2201 (US)**

(74) Representative:  
**Nunney, Ronald Frederick Adolphe et al**  
**Kodak Limited,**  
**Patents, W92-3A,**  
**Headstone Drive**  
**Harrow, Middlesex HA1 4TY (GB)**

(54) **Ink jet recording element**

(57) An ink jet recording element comprising a support having thereon, in the order recited, at least one base layer comprising a hydrophilic or porous material and a porous top layer capable of either retaining or transporting an ink image, the porous top layer comprising a polymeric binder and thermally-compliant core-shell particles, the particle-to-binder ratio being between 95:5 and 50:50, and wherein each thermally-compliant core-shell particle has:

a) a shell of inorganic colloidal particles, and

b) a core of a thermoplastic polymer,

the particles having a particle size between 0.5  $\mu\text{m}$  and 10  $\mu\text{m}$ , the polymeric core having a softening point of greater than 50 ° C, and the weight ratio of the shell of the inorganic colloidal particles to the thermoplastic core being from 1:5 to 1:99.

**EP 1 184 194 A3**



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 01 20 3140

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A,D	EP 0 685 344 A (MITSUBISHI PAPER MILLS LTD) 6 December 1995 (1995-12-06) * page 5, line 11 - page 9, line 49 * * page 11, line 7 - line 30 * * claims 1,11,21; examples 31,48 *	1-10	B41M5/00
A	EP 0 818 322 A (OJI PAPER CO) 14 January 1998 (1998-01-14) * page 2, line 58 - page 3, line 10 * * page 5, line 43 - page 6, line 18 * * page 6, line 36 - page 7, line 10 * * claims 1,2,5,6,8 *	1-10	
A,D	EP 0 631 013 A (ASAHI GLASS CO LTD) 28 December 1994 (1994-12-28) * the whole document *	1-10	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			B41M
The present search report has been drawn up for all claims			
Place of search <b>MUNICH</b>		Date of completion of the search <b>12 September 2002</b>	Examiner <b>Mörsky, S</b>
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons A : member of the same patent family, corresponding document	

EPO FORM 1503 03 82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 20 3140

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

12-09-2002

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 0685344	A	06-12-1995	JP	7101142 A	18-04-1995
			JP	7117335 A	09-05-1995
			JP	8118790 A	14-05-1996
			DE	69510502 D1	05-08-1999
			DE	69510502 T2	27-01-2000
			EP	0685344 A2	06-12-1995
			US	5576088 A	19-11-1996
			US	5750200 A	12-05-1998
EP 0818322	A	14-01-1998	DE	69700580 D1	11-11-1999
			DE	69700580 T2	13-07-2000
			EP	0818322 A1	14-01-1998
			JP	10081065 A	31-03-1998
			US	6335085 B1	01-01-2002
EP 0631013	A	28-12-1994	JP	3264739 B2	11-03-2002
			JP	7082694 A	28-03-1995
			DE	69406986 D1	08-01-1998
			DE	69406986 T2	26-03-1998
			EP	0631013 A1	28-12-1994
			US	5472773 A	05-12-1995

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**THIS PAGE BLANK (USPTO)**